AVERY DENNISON

250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **HPA 1905**
SUPPORT: EPDM FOAM
SUBSTRATE: PP
CERT NO.: 230105 - 1151

ANAB ANSI National Accreditation Board ACCREDITED ISO/IEC 17025 TESTING LABORATORY

CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06
Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
Cellular PVN with PSA

TEST PARAMETERS:

SECTION: **2.1 Heat Aging** — Shrink — ASTM D3575-08*

Specification	Substrate	Results	Status
< 5% 2.1, Heat Aging, 30 mins @ 100° C	ABS	Stable, Less than 5% Length and Width	**Pass**
< 5% 2.1, Heat Aging, 30 mins @ 100° C	E-COATED METAL	Stable, Less than 5% Length and Width	**Pass**
< 5% 2.1, Heat Aging, 30 mins @ 100° C	SS	Stable, Less than 5% Length and Width	**Pass**

SECTION: **2.2 Adhesion**

Specification	Substrate	Results	Status
No Adhesion Loss or Delamiantion 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C, 24 hrs @ 38° C / 95% RH, 72 hrs @ -40° C	ABS	Good, Stable, no Lifting	**Pass**
No Adhesion Loss or Delamiantion 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C, 24 hrs @ 38° C / 95% RH, 72 hrs @ -40° C	E-COATED METAL	Good, Stable, no Lifting	**Pass**
No Adhesion Loss or Delamiantion 2.2, , Cycles (2X) 72 hrs @ 70° C, 24 hrs @ 38° C / 95% RH, 72 hrs @ -40° C	SS	Good, Stable, no Lifting	**Pass**

CERTIFIED BY: Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.