



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 5212
SUPPORT: Ensolite Sf0
SUBSTRATE: Listed
CERT NO.: 240122 - 1332

CHRYSLER MS-AY-522 B TYPE 1
OEM Rev Date: Mar 12
Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
Cellular PVN with PSA



TAPE REQUIREMENTS:

SECTION:	Test	ASTM D3575	Specification	Panel	Results	Status
SECTION: 2.1	Heat Aging	ASTM D3575	< 5% Shrink	ABS	Stable, Less than 5% Length and Width	Pass
2.1,	Heat Aging, 30 mins @ 100° C					
SECTION: 2.1	Heat Aging	ASTM D3575	< 5% Shrink	PP	Stable, Less than 5% Length and Width	Pass
2.1,	Heat Aging, 30 mins @ 100° C					
SECTION: 2.1	Heat Aging	ASTM D3575	< 5% Shrink	PAINTED METAL	Stable, Less than 5% Length and Width	Pass
2.1,	Heat Aging, 30 mins @ 100° C					
SECTION: 2.1	Heat Aging	ASTM D3575	< 5% Shrink	SS	Stable, Less than 5% Length and Width	Pass
2.1,	Heat Aging, 30 mins @ 100° C					
SECTION: 2.2	Adhesion		Specification	Panel	Results	Status
2.2,	Adhesion, Cycles (2X)		No Adhesion Loss or Delamination	ABS	Good, Stable, no Lifting	Pass
	72 hrs @ 70° C					
	24 hrs @ 38° C / 95% RH					
	72 hrs @ -40° C					
SECTION: 2.2	Adhesion		Specification	Panel	Results	Status
2.2,	Adhesion, Cycles (2X)		No Adhesion Loss or Delamination	PP	Good, Stable, no Lifting	Pass
	72 hrs @ 70° C					
	24 hrs @ 38° C / 95% RH					
	72 hrs @ -40° C					
SECTION: 2.2	Adhesion		Specification	Panel	Results	Status
2.2,	Adhesion, Cycles (2X)		No Adhesion Loss or Delamination	PAINTED METAL	Good, Stable, no Lifting	Pass
	72 hrs @ 70° C					
	24 hrs @ 38° C / 95% RH					
	72 hrs @ -40° C					
SECTION: 2.2	Adhesion		Specification	Panel	Results	Status
2.2,	Adhesion, Cycles (2X)		No Adhesion Loss or Delamination	SS	Good, Stable, no Lifting	Pass
	72 hrs @ 70° C					
	24 hrs @ 38° C / 95% RH					
	72 hrs @ -40° C					

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.