



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8302
SUPPORT: PET FOAM
SUBSTRATE: ABS
CERT NO.: 230103 - 0841



CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
Cellular PVN with PSA

TEST PARAMETERS:

SECTION:	2.1 Heat Aging	Shrink	ASTM D3575-08*	Substrate	Results	Status
Specification:	< 5%			ABS	Stable, Less than 5% Length and Width	Pass
2.1, Heat Aging, 30 mins @ 100° C						
Specification:	< 5%			Substrate	Results	Status
2.1, Heat Aging, 30 mins @ 100° C				PP	Stable, Less than 5% Length and Width	Pass
Specification:	< 5%			Substrate	Results	Status
2.1, Heat Aging, 30 mins @ 100° C				E-COATED METAL	Stable, Less than 5% Length and Width	Pass
Specification:	< 5%			Substrate	Results	Status
2.1, Heat Aging, 30 mins @ 100° C				SS	Stable, Less than 5% Length and Width	Pass

SECTION: 2.2 Adhesion

Specification:	No Adhesion Loss or Delamination					
2.2, Adhesion, Cycles (2X)		Substrate			Results	Status
72 hrs @ 70° C		ABS			Good, Stable, no Lifting	Pass
24 hrs @ 38° C / 95% RH						
72 hrs @ -40° C						
Specification:	No Adhesion Loss or Delamination					
2.2, Adhesion, Cycles (2X)	Substrate				Results	Status
72 hrs @ 70° C	PP				Good, Stable, no Lifting	Pass
24 hrs @ 38° C / 95% RH						
72 hrs @ -40° C						
Specification:	No Adhesion Loss or Delamination					
2.2, Adhesion, Cycles (2X)	Substrate				Results	Status
72 hrs @ 70° C	E-COATED METAL				Good, Stable, no Lifting	Pass
24 hrs @ 38° C / 95% RH						
72 hrs @ -40° C						
Specification:	No Adhesion Loss or Delamination					
2.2, , Cycles (2X)	Substrate				Results	Status
72 hrs @ 70° C	SS				Good, Stable, no Lifting	Pass
24 hrs @ 38° C / 95% RH						
72 hrs @ -40° C						

CERTIFIED BY:

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.