



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT B
SUPPORT: EPDM FOAM
SUBSTRATE: E-COATED METAL
CERT NO.: 230103 - 0848



CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
Cellular PVN with PSA

TEST PARAMETERS:

SECTION: 2.1	Heat Aging	Shrink	ASTM D3575-08*			
Specification:	< 5%	Substrate	ABS	Results	Stable, Less than 5% Length and Width	Status Pass
2.1, Heat Aging, 30 mins @ 100° C						
Specification:	< 5%	Substrate	PP	Results	Stable, Less than 5% Length and Width	Status Pass
2.1, Heat Aging, 30 mins @ 100° C						
Specification:	< 5%	Substrate	E-COATED METAL	Results	Stable, Less than 5% Length and Width	Status Pass
2.1, Heat Aging, 30 mins @ 100° C						
Specification:	< 5%	Substrate	SS	Results	Stable, Less than 5% Length and Width	Status Pass
2.1, Heat Aging, 30 mins @ 100° C						
SECTION: 2.2	Adhesion					
Specification:	No Adhesion Loss or Delamination	Substrate	ABS	Results	Good, Stable, no Lifting	Status Pass
2.2, Adhesion, Cycles (2X)						
72 hrs @ 70° C						
24 hrs @ 38° C / 95% RH						
72 hrs @ -40° C						
Specification:	No Adhesion Loss or Delamination	Substrate	PP	Results	Good, Stable, no Lifting	Status Pass
2.2, Adhesion, Cycles (2X)						
72 hrs @ 70° C						
24 hrs @ 38° C / 95% RH						
72 hrs @ -40° C						
Specification:	No Adhesion Loss or Delamination	Substrate	E-COATED METAL	Results	Good, Stable, no Lifting	Status Pass
2.2, Adhesion, Cycles (2X)						
72 hrs @ 70° C						
24 hrs @ 38° C / 95% RH						
72 hrs @ -40° C						
Specification:	No Adhesion Loss or Delamination	Substrate	SS	Results	Good, Stable, no Lifting	Status Pass
2.2, , Cycles (2X)						
72 hrs @ 70° C						
24 hrs @ 38° C / 95% RH						
72 hrs @ -40° C						

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.