



250 Chester Street  
Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT B  
SUPPORT: NITRILE VINYL FOAM  
SUBSTRATE: ABS  
CERT NO.: 230103 - 0848



### CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material  
Cellular PVN with PSA

#### TEST PARAMETERS:

##### SECTION: 2.1 Heat Aging

Specification: < 5%  
2.1, Heat Aging, 30 mins @ 100° C

Shrink ASTM D3575-08\*

##### Substrate

ABS

##### Results

Stable, Less than 5% Length and Width

##### Status

Pass

Specification: < 5%  
2.1, Heat Aging, 30 mins @ 100° C

##### Substrate

PP

##### Results

Stable, Less than 5% Length and Width

##### Status

Pass

Specification: < 5%  
2.1, Heat Aging, 30 mins @ 100° C

##### Substrate

E-COATED METAL

##### Results

Stable, Less than 5% Length and Width

##### Status

Pass

Specification: < 5%  
2.1, Heat Aging, 30 mins @ 100° C

##### Substrate

SS

##### Results

Stable, Less than 5% Length and Width

##### Status

Pass

##### SECTION: 2.2 Adhesion

Specification: No Adhesion Loss or Delamination

2.2, Adhesion, Cycles (2X)  
72 hrs @ 70° C  
24 hrs @ 38° C / 95% RH  
72 hrs @ -40° C

##### Substrate

ABS

##### Results

Good, Stable, no Lifting

##### Status

Pass

Specification: No Adhesion Loss or Delamination

2.2, Adhesion, Cycles (2X)  
72 hrs @ 70° C  
24 hrs @ 38° C / 95% RH  
72 hrs @ -40° C

##### Substrate

PP

##### Results

Good, Stable, no Lifting

##### Status

Pass

Specification: No Adhesion Loss or Delamination

2.2, Adhesion, Cycles (2X)  
72 hrs @ 70° C  
24 hrs @ 38° C / 95% RH  
72 hrs @ -40° C

##### Substrate

E-COATED METAL

##### Results

Good, Stable, no Lifting

##### Status

Pass

Specification: No Adhesion Loss or Delamination

2.2, , Cycles (2X)  
72 hrs @ 70° C  
24 hrs @ 38° C / 95% RH  
72 hrs @ -40° C

##### Substrate

SS

##### Results

Good, Stable, no Lifting

##### Status

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.