



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8327 12 PT BD
SUPPORT: PET FOAM
SUBSTRATE: E-COATED-METAL
CERT NO.: 230103 - 0939



CHRYSLER MS-AY-545 B1

OEM Rev Date: Feb 06

Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
B1 - with Room Temp PSA

TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance

3, Heat Resistance, Type 1 Adhesive
Cycles (2X)
72 hrs @ 70° C
24 hrs @ 38° C / 95% RH
72 hrs @ -40° C

Specification
No Adhesion Loss or Delamination

Results
Good, Stable, No Lifting

Status
Pass

SECTION: 3.0 Heat Resistance

3, Heat Resistance, Type 2 Adhesive
Cycles (2X)
72 hrs @ 79° C
24 hrs @ 38° C / 95% RH
72 hrs @ -40° C

Specification
No Adhesion Loss or Delamination

Results
Good, Stable, No Lifting

Status
Pass

SECTION: 3.4 Adhesion Test

3.4, Adhesion Test, 20 mins @ RT

ASTM D903-98

Specification

0.9 N / cm

Results

10.1

Status
Pass

SECTION: 3.6 Flammability

3.6, Flammability, Initial, As Component

FMVSS 302

Specification

100 mm / minute

Results

EBRZT

Status
Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.