



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBA 1960 12 PT BD
SUPPORT: NITRILE VINYL FOAM
SUBSTRATE: E-COATED METAL
CERT NO.: 230103 - 0944

CHRYSLER MS-AY-545 B2

OEM Rev Date: Oct 10

Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
B2 - with High Temp PSA



TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance

3, Heat Resistance, Type 1 Adhesive
Cycles (2X)
72 hrs @ 70° C
24 hrs @ 38° C / 95% RH
72 hrs @ -40° C

| <u>Specification</u> | <u>Results</u> | <u>Status</u> |
|----------------------------------|--------------------------|---------------|
| No Adhesion Loss or Delamination | Good, Stable, No Lifting | Pass |

SECTION: 3.0 Heat Resistance

3, Heat Resistance, Type 2 Adhesive
Cycles (2X)
72 hrs @ 79° C
24 hrs @ 38° C / 95% RH
72 hrs @ -40° C

| <u>Specification</u> | <u>Results</u> | <u>Status</u> |
|----------------------------------|--------------------------|---------------|
| No Adhesion Loss or Delamination | Good, Stable, No Lifting | Pass |

SECTION: 3.4 Adhesion Test

3.4, Adhesion Test, 20 mins @ RT

ASTM D903-98 10

Specification

0.9 N / cm

Results

4.1

Status

Pass

SECTION: 3.6 Flammability

3.6, Flammability, Initial, As Component

FMVSS 302 09

Specification

100 mm / minute

Results

EBRTZ

Status

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.