



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBA 1960
SUPPORT: NITRILE VINYL FOAM
SUBSTRATE: PP
CERT NO.: 230103 - 0943

CHRYSLER MS-AY-545 B2

OEM Rev Date: Oct 10

Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
B2 - with High Temp PSA



TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance

3, Heat Resistance, Type 1 Adhesive
Cycles (2X)
72 hrs @ 70° C
24 hrs @ 38° C / 95% RH
72 hrs @ -40° C

Specification
No Adhesion Loss or Delamination

Results
Good, Stable, No Lifting

Status
Pass

SECTION: 3.0 Heat Resistance

3, Heat Resistance, Type 2 Adhesive
Cycles (2X)
72 hrs @ 79° C
24 hrs @ 38° C / 95% RH
72 hrs @ -40° C

Specification
No Adhesion Loss or Delamination

Results
Good, Stable, No Lifting

Status
Pass

SECTION: 3.4 Adhesion Test

3.4, Adhesion Test, 20 mins @ RT

ASTM D903-98 10

Specification

0.9 N / cm

Results

6.1

Status
Pass

SECTION: 3.6 Flammability

3.6, Flammability, Initial, As Component

FMVSS 302 09

Specification

100 mm / minute

Results

EBRTZ

Status
Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date: 4-20-2012 Page 1 of 1