



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: stus.averydennison.com

TEST REPORT

PRODUCT: FBR 1950 12 PT BD
SUPPORT: EPDM FOAM
SUBSTRATE: ABS
STD CERT NO.: 230103 - 0944



CHRYSLER MS-AY-545 C1
OEM Rev Date: Oct 10
Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
C1 - with Room Temp PSA and backing

TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance	Specification	Results	Status
3, Heat Resistance, Type 1 Adhesive	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass
Cycles (2X)			
72 hrs @ 70° C			
24 hrs @ 38° C / 95% RH			
72 hrs @ -40° C			

SECTION: 3.0 Heat Resistance	Specification	Results	Status
3, Heat Resistance, Type 2 Adhesive	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass
Cycles (2X)			
72 hrs @ 79° C			
24 hrs @ 38° C / 95% RH			
72 hrs @ -40° C			

SECTION: 3.4 Adhesion Test	Specification	Results	Status
3.4, Adhesion Test, 20 mins @ RT	0.9 N / cm	6.0	Pass

ASTM D903-98 10

SECTION: 3.6 Flammability	Specification	Results	Status
3.6, Flammability, Initial, As Component	100 mm / minute	< B 25	Pass

FMVSS 302 09

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.