



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: stus.averydennison.com

## TEST REPORT

PRODUCT: FBR 1950 12 PT BD  
SUPPORT: EPDM FOAM  
SUBSTRATE: E-COATED METAL  
STD CERT NO.: 230103 - 0945

CHRYSLER MS-AY-545 C1

OEM Rev Date: Oct 10

Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation  
C1 - with Room Temp PSA and backing



### TAPE REQUIREMENTS:

#### SECTION: 3.0 Heat Resistance

3, Heat Resistance, Type 1 Adhesive  
Cycles (2X)  
72 hrs @ 70° C  
24 hrs @ 38° C / 95% RH  
72 hrs @ -40° C

Specification  
No Adhesion Loss or Delamination

Results  
Good, Stable, No Lifting

Status  
Pass

#### SECTION: 3.0 Heat Resistance

3, Heat Resistance, Type 2 Adhesive  
Cycles (2X)  
72 hrs @ 79° C  
24 hrs @ 38° C / 95% RH  
72 hrs @ -40° C

Specification  
No Adhesion Loss or Delamination

Results  
Good, Stable, No Lifting

Status  
Pass

#### SECTION: 3.4 Adhesion Test

3.4, Adhesion Test, 20 mins @ RT

ASTM D903-98 10

Specification  
0.9 N / cm

Results  
5.8

Status  
Pass

#### SECTION: 3.6 Flammability

3.6, Flammability, Initial, As Component

FMVSS 302 09

Specification  
100 mm / minute

Results  
EBRTZ

Status  
Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date: 4-9-2012 Page 1 of 1