



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: stus.averydennison.com

TEST REPORT  
PRODUCT: FT 8327 12 PT BD  
SUPPORT: PET FOAM  
SUBSTRATE: E-COATED-METAL  
STD CERT NO.: 230103 - 0939



CHRYSLER MS-AY-545 C1  
OEM Rev Date: Feb 06  
Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation  
C1 - with Room Temp PSA and backing

**TAPE REQUIREMENTS:**

**SECTION: 3.0 Heat Resistance**

3, Heat Resistance, Type 1 Adhesive  
Cycles (2X)  
72 hrs @ 70° C  
24 hrs @ 38° C / 95% RH  
72 hrs @ -40° C

**Specification**  
**No Adhesion Loss or Delamination**

**Results**  
Good, Stable, No Lifting

**Status**  
**Pass**

**SECTION: 3.0 Heat Resistance**

3, Heat Resistance, Type 2 Adhesive  
Cycles (2X)  
72 hrs @ 79° C  
24 hrs @ 38° C / 95% RH  
72 hrs @ -40° C

**Specification**  
**No Adhesion Loss or Delamination**

**Results**  
Good, Stable, No Lifting

**Status**  
**Pass**

**SECTION: 3.4 Adhesion Test**

3.4, Adhesion Test, 20 mins @ RT

ASTM D903-98

**Specification**

**0.9 N / cm**

**Results**

10.1

**Status**  
**Pass**

**SECTION: 3.6 Flammability**

3.6, Flammability, Initial, As Component

FMVSS 302

**Specification**

**100 mm / minute**

**Results**

EBRZT

**Status**  
**Pass**

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.