



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBA 1960 12 PT BD
SUPPORT: NITRILE VINYL FOAM
SUBSTRATE: E-COATED METAL
CERT NO.: 230103 - 0946



CHRYSLER MS-AY-545 C2
OEM Rev Date: Oct 10
Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation
C2 - with High Temp PSA and backing

TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance	Specification	Results	Status
3, Heat Resistance, Type 1 Adhesive	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass
Cycles (2X)			
72 hrs @ 70° C			
24 hrs @ 38° C / 95% RH			
72 hrs @ -40° C			

SECTION: 3.0 Heat Resistance	Specification	Results	Status
3, Heat Resistance, Type 2 Adhesive	No Adhesion Loss or Delamination	Good, Stable, No Lifting	Pass
Cycles (2X)			
72 hrs @ 79° C			
24 hrs @ 38° C / 95% RH			
72 hrs @ -40° C			

SECTION: 3.4 Adhesion Test	ASTM D903-98 10	Specification	Results	Status
3.4, Adhesion Test, 20 mins @ RT		0.9 N / cm	4.1	Pass

SECTION: 3.6 Flammability	FMVSS 302 09	Specification	Results	Status
3.6, Flammability, Initial, As Component		100 mm / minute	EBRTZ	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.