



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FBA 1960  
SUPPORT: EPDM FOAM  
SUBSTRATE: E-COATED METAL  
CERT NO.: 230103 - 0945



CHRYSLER MS-AY-545 C2  
OEM Rev Date: Oct 10  
Cellular Polyurethane - 6 lb Density - Light / Dust Seal, Noise Attenuation  
C2 - with High Temp PSA and backing

### TAPE REQUIREMENTS:

#### SECTION: 3.0 Heat Resistance

3, Heat Resistance, Type 1 Adhesive  
Cycles (2X)  
72 hrs @ 70° C  
24 hrs @ 38° C / 95% RH  
72 hrs @ -40° C

#### Specification

No Adhesion Loss or Delamination

#### Results

Good, Stable, No Lifting

#### Status

Pass

#### SECTION: 3.0 Heat Resistance

3, Heat Resistance, Type 2 Adhesive  
Cycles (2X)  
72 hrs @ 79° C  
24 hrs @ 38° C / 95% RH  
72 hrs @ -40° C

#### Specification

No Adhesion Loss or Delamination

#### Results

Good, Stable, No Lifting

#### Status

Pass

#### SECTION: 3.4 Adhesion Test

3.4, Adhesion Test, 20 mins @ RT

ASTM D903-98 10

#### Specification

0.9 N / cm

#### Results

4.2

#### Status

Pass

#### SECTION: 3.6 Flammability

3.6, Flammability, Initial, As Component

FMVSS 302 09

#### Specification

100 mm / minute

#### Results

EBRTZ

#### Status

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.