



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **FT 3043**
SUPPORT: **Poron 4701-40-15375-04**
SUBSTRATE: **PP**
CERT NO.: **251217 - 0924**

MS-AY-549-B2
OEM Rev Date: May 18
Microcellular Polyurethane - High Density
Grade 2



TAPE REQUIREMENTS:

Original Properties

SECTION: 1. Tensile Strength

	ASTM D3574E	Specification	Results	Status
Tensile		275 kPa min	249.2	Fail
Elongation		100 % min	135.9	Pass

SECTION: 1. Tear Resistance

	ASTM D624 Die C	Specification	Results	Status
1. Tear Resistance		0.5 kN/m min	0.0018	Fail

SECTION: 5. Odor*

	Specification	Results	Status
Odor, 22 hrs @ 70°C	No Disagreeable or Offensive Odor	Not Tested	Not Tested

SECTION: 7. Fogging

	SAE J1756	Specification	Results	Status
3 hrs @ 100°C - 21°C Cooling, 1 hr @ RT		60 Units min	92.8	Pass

SECTION: 9. Adhesion Testing

	Specification	Results	Status
Thermo Cycling 72 hrs @ 80°C 22 hrs @ 38°C / 95% RH 22 hrs @ -40°C	No Shrink, Loss of Adhesion or Detrimental Effect	No Lifting, Shrink or Loss of Adhesion	Pass

SECTION: 11. Burn Rate

	FMVSS 302	Specification	Results	Status
Burn Rate - Plaques		100 mm / min	SE	Pass

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.