



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 1123  
SUPPORT: 10 MIL CLEAR UHMWPE  
SUBSTRATE: E-COATED-METAL  
CERT NO.: 230103 - 0949

CHRYSLER MS-CH-612

OEM Rev Date: Oct 04

Adhesive Requirements, Pressure Sensitive Adhesive  
Low Friction



### TEST PARAMETERS:

| SECTION: <b>6.3 Tensile Strength</b><br>6.3, Tensile Strength, A. Initial @ RT  | CLP 463TB-4-01*  | <u>Specification</u><br><b>35 N / cm</b>  | <u>Results</u><br><b>97.6</b>  | <u>Status</u><br><b>Pass</b> |
|---|------------------|---|--------------------------------|------------------------------|
| SECTION: <b>6.3 Peel Adhesion</b><br>6.3, Peel Adhesion, B. Initial @ RT  | CLP 463TB-3-01*  | <u>Specification</u><br><b>3.5 N / cm</b> | <u>Results</u><br><b>4.6</b>   | <u>Status</u><br><b>Pass</b> |
| SECTION: <b>6.3 Peel Adhesion</b><br>6.3, Peel Adhesion, B. 168 hrs @ 79° C   | CLP 463CB-10-01* | <u>Specification</u><br><b>3.5 N / cm</b> | <u>Results</u><br><b>10.8</b>  | <u>Status</u><br><b>Pass</b> |
| SECTION: <b>6.3 Peel Adhesion</b><br>6.3, Peel Adhesion, B. 168 hrs @ 38° C / 95% RH  | ASTM D1735       | <u>Specification</u><br><b>3.5 N / cm</b> | <u>Results</u><br><b>9.1</b>   | <u>Status</u><br><b>Pass</b> |
| SECTION: <b>6.3 Peel Adhesion</b><br>6.3, Peel Adhesion, B. Cycles (2X)<br>24 hrs @ 79° C<br>24 hrs @ 38° C / 95% RH<br>24 hrs @ -29° C | CLP 463CB-10-01* | <u>Specification</u><br><b>3.5 N / cm</b> | <u>Results</u><br><b>9.6</b>   | <u>Status</u><br><b>Pass</b> |
| SECTION: <b>6.3 Shear Adhesion</b><br>6.3, Shear Adhesion, C. Initial @ RT  | CLP 463TB-8-01*  | <u>Specification</u><br><b>104 kPa</b>    | <u>Results</u><br><b>261.6</b> | <u>Status</u><br><b>Pass</b> |

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.