



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1123
SUPPORT: 5 Mil BLACK UHMWPE
SUBSTRATE: ABS
CERT NO.: 230103 - 0948

CHRYSLER MS-CH-612

OEM Rev Date: Oct 04
Adhesive Requirements, Pressure Sensitive Adhesive
Low Friction



TEST PARAMETERS:

SECTION: 6.3 Tensile Strength	CLP 463TB-4-01*	<u>Specification</u> 35 N / cm	<u>Results</u> 44.2	<u>Status</u> Pass
6.3, Tensile Strength, A. Initial @ RT				
SECTION: 6.3 Peel Adhesion	CLP 463TB-3-01*	<u>Specification</u> 3.5 N / cm	<u>Results</u> 10.3	<u>Status</u> Pass
6.3, Peel Adhesion, B. Initial @ RT				
SECTION: 6.3 Peel Adhesion	CLP 463CB-10-01*	<u>Specification</u> 3.5 N / cm	<u>Results</u> 9.5	<u>Status</u> Pass
6.3, Peel Adhesion, B. 168 hrs @ 79° C				
SECTION: 6.3 Peel Adhesion	ASTM D1735	<u>Specification</u> 3.5 N / cm	<u>Results</u> 14.5	<u>Status</u> Pass
6.3, Peel Adhesion, B. 168 hrs @ 38° C / 95% RH				
SECTION: 6.3 Peel Adhesion	CLP 463CB-10-01*	<u>Specification</u> 3.5 N / cm	<u>Results</u> 7.4	<u>Status</u> Pass
6.3, Peel Adhesion, B. Cycles (2X)				
24 hrs @ 79° C				
24 hrs @ 38° C / 95% RH				
24 hrs @ -29° C				
SECTION: 6.3 Shear Adhesion	CLP 463TB-8-01*	<u>Specification</u> 104 kPa	<u>Results</u> 174.1	<u>Status</u> Pass
6.3, Shear Adhesion, C. Initial @ RT				

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.