



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: [psa.tape@averydennison.com](mailto:psa.tape@averydennison.com)  
URL: [tapes.averydennison.com](http://tapes.averydennison.com)

## TEST REPORT

PRODUCT: FT 8392 12 PT BD  
SUPPORT: PVC FOAM  
SUBSTRATE: PP  
CERT NO.: 230103 - 1010

FCA MS-AY-500-B -TYPE-3  
CHRYSLER MS-AY-355 Apr 06  
Cellular Polyvinyl Chloride (PVC)  
B - Cellular Vinyl with Pressure Sensitive adhesive (PSA)



### TAPE REQUIREMENTS:

#### Adhesive Requirements Table 2

SECTION:	TEST	Specification	Results	Status
4. Heat Aging	ASTM D573	No Shrink, Loss of Adhesion or Detrimental Effect	No Lift, Separation or Adhesion Loss	Pass
4. 70 hrs @ 70°C				
6. Odor	SAE J1351	Specification	Results	Status
Dry, 1 hr @ 79°C		No Offensive Odor	2 - Slight, But Noticeable Odor	Pass
Wet, 1 hr @ 79°C - Deionized Water		No Offensive Odor	2 - Slight, But Noticeable Odor	Pass
8. Adhesion	ASTM D903	Specification	Results	Status
8. Original, 20 mins after Application		274 N / m	369.8	Pass
8. After Two Environment Cycles		274 N / m	1406.4	Pass
8. After Thermo-Cycling		Specification	Results	Status
8. After Two Environment Cycles Cycles (2x)		No Shrink, Loss of Adhesion or Detrimental Effect	No Lift, Separation or Adhesion Loss	Pass
72 hrs @ 70°C				
24 hrs @ 38°C / 100% RH				
24 hrs @ -29°C				
9. Burn Rate	FMVSS 302	Specification	Results	Status
Initial, Component		< 100 mm / min	< B 25	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.