



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126
SUPPORT: FOAM BACKED VINYL
SUBSTRATE: FIBER BOARD
CERT NO.: 230103 - 0951



FCA MS-CB-134

OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System
Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid substrate with the application of pressure.

TEST PARAMETERS:

SECTION: 3.2 Adhesive Peel Strength		Specification	Results	Status
Initial, 24 hrs @ RT		2.7 N / cm	4.3	Pass
SECTION: 3.2 Adhesive Peel Strength	LP-463CB-10-01	Specification	Results	Status
168 hrs @ 79°C		1.8 N / cm	6.6	Pass
SECTION: 3.2 Adhesive Peel Strength	ASTM D17363CB-10-01	Specification	Results	Status
168 hrs @ 38°C / 98% RH		2.2 N / cm	4.2	Pass
SECTION: 3.2 Adhesive Peel Strength	LP-463CB-10-01	Specification	Results	Status
Cycles, 3X		2.2 N / cm	5.6	Pass
24 hrs @ 79°C				
24 hrs @ 38°C / 95% RH				
24 hrs @ -29°C				
SECTION: 3.3 Shear Adhesion		Specification	Results	Status
Initial, 24 hrs @ RT		55 kPa	95.1	Pass
SECTION: 3.3 Shear Adhesion	LP-463CB-10-01	Specification	Results	Status
168 hrs @ 79°C		48 kPa	105.6	Pass
SECTION: 3.3 Shear Adhesion	ASTM D1735	Specification	Results	Status
168 hrs @ 38°C / 98% RH		55 kPa	102.1	Pass
SECTION: 3.3 Shear Adhesion	LP-463CB-10-01	Specification	Results	Status
Cycles, 3X		55 kPa	89.2	Pass
24 hrs @ 79°C				
24 hrs @ 38°C / 95% RH				
24 hrs @ -29°C				

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.