



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 1126 12 PT BD  
SUPPORT: 0.5 MM SCRIM FELT  
SUBSTRATE: ABS  
CERT NO.: 230103 - 1038

FCA MS-JZ-8-22  
OEM Rev Date: Dec 16  
Anti-Squeak Fabric, Pressure Sensitive



### TAPE REQUIREMENTS:

#### SECTION: Wear Resistance

Taber Abrasion, Dry, 1000 Cycles, CS-10, 1000 g Load

ASTM D3884

Specification  
No Noticeable Wear or  
Adhesive / Fiber Loosening  
No Noticeable Wear or  
Adhesive / Fiber Loosening

Results  
No Loosening of Fibers or Adhesive

Status  
Pass

Taber Abrasion, Wet, 1000 Cycles, CS-10, 500 g Load

No Loosening of Fibers or Adhesive

Pass

#### SECTION: Odor

Dry, 1 hr @ 79°C

ASTM J1351

Specification  
No Disagreeable Odor

Results  
2 - Slight, But Noticeable Odor

Status  
Pass

Wet, 1 hr @ 79°C - Deionized Water

Specification  
No Disagreeable Odor

Results  
2 - Slight, But Noticeable Odor

Pass

#### SECTION: Flammability

Initial, Component

FMVSS 302

Specification  
< 101.6 mm / min

Results  
< B 50

Status  
Pass

#### SECTION: Tape Tests

A. Original, 20 mins @ RT, Tape Tests,

LP-463LB-19-01

Specification  
No Adhesive Lifting

Results  
Good, Stable, No Lifting

Status  
Pass

B. 168 hours @ 110°C, Tape Tests,

Specification  
No Adhesive Lifting

Results  
Good, Stable, No Lifting

Pass

C. Cycles (2X), Tape Tests,

16 hrs @ 38°C / 95% RH  
24 hrs @ 110°C  
6 hrs @ -29°C

Specification  
No Adhesive Lifting

Results  
Good, Stable, No Lifting

Pass

D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Tape Tests,

Specification  
No Adhesive Lifting

Results  
Good, Stable, No Lifting

Pass

#### SECTION: Bond Peel Tests

A. Original, 20 mins @ RT, Bond Peel Tests,

ASTM D1000

Specification  
7 N / cm

Results  
10.0

Status  
Pass

B. 168 hours @ 110°C, Bond Peel Tests,

Specification  
8 N / cm

8.7

Pass

C. Cycles (2X), Bond Peel Tests,

16 hrs @ 38°C / 95% RH  
24 hrs @ 110°C  
6 hrs @ -29°C

Specification  
9.5 N / cm

10.4

Pass

D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Bond Peel Test

Specification  
9 N / cm

11.3

Pass

#### SECTION: Resistance to Non-Condensing Humidity

Resistance to Non-Condensing Humidity

LP-463KB-12-01

Specification  
No Fade, Color Changes  
or Loosening of Fibers

Results  
Not Tested

Status  
Not Tested

#### SECTION: Resistance to Crocking Wet / Dry

Resistance to Crocking Wet

SAE J861

Specification  
4 Min Rating

Results  
Not Tested

Status  
Not Tested

Resistance to Crocking Dry

Specification  
4 Min Rating

Results  
Not Tested

Status  
Not Tested

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.