



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126 12 PT BD
SUPPORT: 0.5 MM SCRIM FELT
SUBSTRATE: PP
CERT NO.: 230103 - 1038

FCA MS-JZ-8-22
OEM Rev Date: Dec 16
Anti-Squeak Fabric, Pressure Sensitive



TAPE REQUIREMENTS:

SECTION: Wear Resistance

Taber Abrasion, Dry, 1000 Cycles, CS-10, 1000 g Load

ASTM D3884

Specification

No Noticeable Wear or
Adhesive / Fiber Loosening

Results

No Loosening of Fibers or Adhesive

Status

Pass

Taber Abrasion, Wet, 1000 Cycles, CS-10, 500 g Load

No Noticeable Wear or
Adhesive / Fiber Loosening

No Loosening of Fibers or Adhesive

Pass

SECTION: Odor

Dry, 1 hr @ 79°C

ASTM J1351

Specification

No Disagreeable Odor

Results

2 - Slight, But Noticeable Odor

Status

Pass

Wet, 1 hr @ 79°C - Deionized Water

No Disagreeable Odor

2 - Slight, But Noticeable Odor

Pass

SECTION: Flammability

Initial, Component

FMVSS 302

Specification

< 101.6 mm / min

Results

< B 25

Status

Pass

SECTION: Tape Tests

A. Original, 20 mins @ RT, Tape Tests,

LP-463LB-19-01

Specification

No Adhesive Lifting

Results

Good, Stable, No Lifting

Status

Pass

B. 168 hours @ 110°C, Tape Tests,

No Adhesive Lifting

Good, Stable, No Lifting

Pass

C. Cycles (2X), Tape Tests,

16 hrs @ 38°C / 95% RH
24 hrs @ 110°C
6 hrs @ -29°C

No Adhesive Lifting

Good, Stable, No Lifting

Pass

D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Tape Tests,

No Adhesive Lifting

Good, Stable, No Lifting

Pass

SECTION: Bond Peel Tests

A. Original, 20 mins @ RT, Bond Peel Tests,

ASTM D1000

Specification

5.5 N / cm

Results

8.8

Status

Pass

B. 168 hours @ 110°C, Bond Peel Tests,

4 N / cm

5.9

Pass

C. Cycles (2X), Bond Peel Tests,

16 hrs @ 38°C / 95% RH
24 hrs @ 110°C
6 hrs @ -29°C

3.5 N / cm

6.9

Pass

D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Bond Peel Test

3.5 N / cm

11.2

Pass

SECTION: Resistance to Non-Condensing Humidity

Resistance to Non-Condensing Humidity

LP-463KB-12-01

Specification

No fade, color changes or
loosening of fibers

Results

Not Tested

Status

Not Tested

SECTION: Resistance to Crocking Wet / Dry

Resistance to Crocking Wet

SAE J861

Specification

4 Min Rating

Results

Not Tested

Status

Not Tested

Resistance to Crocking Dry

4 Min Rating

Not Tested

Not Tested

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.