



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

PRODUCT: **A915-80**
SUPPORT: **FLOCK**
SUBSTRATE: **ABS**
CERT NO.: **230103 - 1031**



FCA MS-JZ-8-22
OEM Rev Date: Dec 16
Anti-Squeak Fabric, Pressure Sensitive

TAPE REQUIREMENTS:

SECTION:	ASTM	Specification	Results	Status
Wear Resistance Taber Abrasion, Dry, 1000 Cycles, CS-10, 1000 g Load	ASTM D3884	No Noticeable Wear or Adhesive / Fiber Loosening	Some Wear But No Fiber Loosening	Pass
Taber Abrasion, Wet, 1000 Cycles, CS-10, 500 g Load		No Noticeable Wear or Adhesive / Fiber Loosening	No Loosening of Fibers or Adhesive	Pass
Odor Dry, 1 hr @ 79°C	ASTM J1351	No Disagreeable Odor	2 - Slight, But Noticeable Odor	Pass
Wet, 1 hr @ 79°C - Deionized Water		No Disagreeable Odor	2 - Slight, But Noticeable Odor	Pass
Flammability Initial, Component	FMVSS 302	< 101.6 mm / min	< B 25	Pass
Tape Tests A. Original, 20 mins @ RT, Tape Tests,	LP-463LB-19-01	No Adhesive Lifting	Good, Stable, No Lifting	Pass
B. 168 hours @ 110°C, Tape Tests,		No Adhesive Lifting	Good, Stable, No Lifting	Pass
C. Cycles (2X), Tape Tests, 16 hrs @ 38°C / 95% RH 24 hrs @ 110°C 6 hrs @ -29°C		No Adhesive Lifting	Good, Stable, No Lifting	Pass
D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Tape Tests, 24		No Adhesive Lifting	Good, Stable, No Lifting	Pass
Bond Peel Tests A. Original, 20 mins @ RT, Bond Peel Tests,	ASTM D1000	7 N / cm	7.2	Pass
B. 168 hours @ 110°C, Bond Peel Tests,		8 N / cm	11.0	Pass
C. Cycles (2X), Bond Peel Tests, 16 hrs @ 38°C / 95% RH 24 hrs @ 110°C 6 hrs @ -29°C		9.5 N / cm	13.1	Pass
D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Bond Peel Test		9 N / cm	15.0	Pass
Resistance to Non-Condensing Humidity Resistance to Non-Condensing Humidity <i>As Reported by Supplier</i>	LP-463KB-12-01	No Fade, Color Changes or Loosening of Fibers	Not Tested	Not Tested
Resistance to Crocking Wet / Dry Resistance to Crocking Wet <i>As Reported by Supplier</i>	SAE J861	4 Min Rating	Not Tested	Not Tested
Resistance to Crocking Dry		4 Min Rating	Not Tested	Not Tested

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.