



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **FT 1126 12 PT BD**
SUPPORT: **9.4 MM PORON FOAM**
SUBSTRATE: **TPE**
CERT NO.: 230103 - 1107

FCA PF.90175
OEM Rev Date: Jun 17
Pressure Sensitive Adhesives
Includes Chrysler Standard PF-10770
Table 2 Flexible Composites



TAPE REQUIREMENTS:

SECTION: 3.0 Heat Resistance	LP-463-TB-03-01*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.2, Heat Resistance, Initial, 2 hrs @ RT		No Adhesion Loss or Lifting	Good, Stable, No Staining or Removal	Pass
SECTION: 3.0 Heat Resistance	LP-463-CB-10-01*			
2.2, Heat Resistance, 168 hrs @ 79°C		No Adhesion Loss or Lifting	Good, Stable, No Staining or Removal	Pass
SECTION: 3.0 Heat Resistance	LP-463-CB-10-01*			
2.2, Heat Resistance, 8 hrs @ 93°C"		No Adhesion Loss or Lifting	Good, Stable, No Staining or Removal	Pass
SECTION: 3.0 Heat Resistance				
2.2, Heat Resistance, 24 hrs Water Immersion		No Adhesion Loss or Lifting	Good, Stable, No Staining or Removal	Pass
SECTION: 3.0 Heat Resistance	ASTM D1735			
2.2, Heat Resistance, Cycles (5x)		No Adhesion Loss or Lifting	Good, Stable, No Staining or Removal	Pass
72 hrs @ 70°C				
24 hrs @ 38°C / 95% RH				
24 hrs @ -29°C				
SECTION: 3.0 Peel Adhesion	LP-463-TB-03-01*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.0, Adhesion, Initial, 2 hrs @ RT		0.9 N / cm	5.8	Pass
SECTION: 3.0 Peel Adhesion	LP-463-CB-10-01*			
3.0, Adhesion, 168 hrs @ 79°C		3.3 N / cm	8.2	Pass
SECTION: 3.0 Peel Adhesion	LP-463-CB-10-01*			
3.0, Adhesion, 8 hrs @ 93°C		3.3 N / cm	6.1	Pass
SECTION: 3.0 Peel Adhesion				
3.0, Adhesion, 24 hr Water Immersion		3.3 N / cm	7.3	Pass
SECTION: 3.0 Peel Adhesion	ASTM D1735			
3.0, Adhesion, Heat Resistance, Cycles (5x)		3.3 N / cm	4.6	Pass
Adhesion, Heat Resistance, Cycles (5x)				
72 hrs @ 70°C				
24 hrs @ 38°C / 95% RH				

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.