



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBA 8960
SUPPORT: LOW PERM FOAM
SUBSTRATE: E-COATED-METAL
CERT NO.: 230103 - 1137



FCA PF.90175
OEM Rev Date: Mar 15
Pressure Sensitive Adhesives
Includes Chrysler Standard PF-10770
Table 2 Flexible Composites

TAPE REQUIREMENTS:

SECTION:	Specification	Results	Status
3.0 Heat Resistance 2.2, Heat Resistance, Initial, 2 hrs @ RT	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
3.0 Heat Resistance 2.2, Heat Resistance, 168 hrs @ 79°C	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
3.0 Heat Resistance 2.2, Heat Resistance, 8 hrs @ 93°C	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
3.0 Heat Resistance 2.2, Heat Resistance, 24 hrs Water Immersion	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
3.0 Heat Resistance 2.2, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
3.0 Peel Adhesion 3.0, Adhesion, Initial, 2 hrs @ RT	0.9 N / cm	6.4	Pass
3.0 Peel Adhesion 3.0, Adhesion, 168 hrs @ 79°C	3.3 N / cm	10.8	Pass
3.0 Peel Adhesion 3.0, Adhesion, 8 hrs @ 93°C	3.3 N / cm	10.5	Pass
3.0 Peel Adhesion 3.0, Adhesion, 24 hr Water Immersion	3.3 N / cm	6.8	Pass
3.0 Peel Adhesion 3.0, Adhesion, Heat Resistance, Cycles (5x) Adhesion, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH	3.3 N / cm	10.9	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.