



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FBA 8960 12 PT BD
SUPPORT: LOW PERM FOAM
SUBSTRATE: ABS
CERT NO.: 221209 - 1039

FORD ESA-M11P19-A

OEM Rev Date: Jun 07

Adhesion Requirements

Polyurethane Foam to Polypropylene - Pressure Sensitive Film



TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials

SECTION 3.1 Peel Strength, Plastic Membrane to Panel

3.1.1, As Received ASTM D3330

Specification

0.44 N / mm

ASTM D3330

Results

0.62

Status

Pass

SECTION 3.1 Peel Strength, Plastic Membrane to Panel

3.1.2, Aged, Heat Aged, 7 days @ 88°C ASTM D3330

Specification

0.44 N / mm

ASTM D3330

Results

0.91

Status

Pass

SECTION 3.1 Peel Strength, Plastic Membrane to Panel

3.1.2, Humidity, 7 days @ 37°C / 95% RH ASTM D3330

Specification

0.44 N / mm

ASTM D3330

Results

0.47

Status

Pass

SECTION 3.2 Peel Strength, Foam to Plastic Membrane

3.2.1, Foam to Plastic Membrane, As Received ASTM D903

Specification

No Delamination

ASTM D903

Results

Foam Tearing

Status

Pass

SECTION 3.3 Bond Separation

3.3, 200 gram load, 1 hr @ RT

Specification

No Separation of Bond

Results

3.2

Status

Pass

SECTION 3.4 Quality

3.4, Liner

Specification

Readily Removable

Results

Easily Removed

Status

Pass

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.