TEST REPORT

AVERY DENNISON
250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

PRODUCT: **FT B EZ**
SUPPORT: EPDM FOAM
SUBSTRATE: ABS
CERT NO.: 221209 - 0914

FORD ESA-M11P19-A
OEM Rev Date: Jun 07
Adhesion Requirements

Polyurethane Foam to Polypropylene - Pressure Sensitive Film

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials

	Specification		Results	Status
SECTION **3.1** **Peel Strength, Plastic Membrane to Panel**		ASTM D903-98		
3.1.1, As Received	**0.44 N / mm**		0.9	**Pass**
SECTION **3.1** **Peel Strength, Plastic Membrane to Panel**				
3.1.2, Aged, Heat Aged, 7 days @ 88ºC	**0.44 N / mm**		1.0	**Pass**
SECTION **3.1** **Peel Strength, Plastic Membrane to Panel**				
3.1.2, Humidity, 7 days @ 37ºC / 95% RH	**0.44 N / mm**		0.7	**Pass**
SECTION **3.2** **Peel Strength, Foam to Plastic Membrane**				
3.2.1, Foam to Plastic Membrane, As Received	**No Delamination**		Foam Tearing	**Pass**
SECTION **3.3** **Bond Separation**				
3.3, 200 gram load, 1 hr @ RT	**No Separation of Bond**		No Slip	**Pass**
SECTION **3.4** **Quality**				
	Readily Removable		Easily Removed	**Pass**

CERTIFIED BY: Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°Fand 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.