TEST REPORT

AVERY DENNISON
250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

PRODUCT: **FT B EZ**
SUPPORT: SUPERSEAL FOAM
SUBSTRATE: ABS
CERT NO.: 221209 - 0914

FORD ESA-M11P19-A
OEM Rev Date: Jun 07
Adhesion Requirements
Polyurethane Foam to Polypropylene - Pressure Sensitive Film

ANAB ANSI National Accreditation Board ACCREDITED ISO/IEC 17025 TESTING LABORATORY

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials

SECTION **3.1** **Peel Strength, Plastic Membrane to Panel** 3.1.1, As Received	**Specification** **0.44 N / mm**	ASTM D903	**Results** 2.1	**Status** **Pass**
SECTION **3.1** **Peel Strength, Plastic Membrane to Panel** 3.1.2, Aged, Heat Aged, 7 days @ 88ºC	**Specification** **0.44 N / mm**	ASTM D903	**Results** 1.8	**Status** **Pass**
SECTION **3.1** **Peel Strength, Plastic Membrane to Panel** 3.1.2, Humidity, 7 days @ 37ºC / 95% RH	**Specification** **0.44 N / mm**	ASTM D903	**Results** 2.4	**Status** **Pass**
SECTION **3.2** **Peel Strength, Foam to Plastic Membrane** 3.2.1, Foam to Plastic Membrane, As Received	**Specification** **No Delamination**	ASTM D903	**Results** Foam Tearing	**Status** **Pass**
SECTION **3.3** **Bond Separation** 3.3, 200 gram load, 1 hr @ RT	**Specification** **No Separation of Bond**	ASTM D1000	**Results** No Slip	**Status** **Pass**

CERTIFIED BY: Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.