



250 Chester Street  
Painesville, Ohio 44077

Phone: **866-GO-AVERY (866-462-8379)**  
Fax: **888-358-4469**  
email: **psa.tape@averydennison.com**  
URL: **tapes.averydennison.com**

## TEST REPORT

PRODUCT: **FT 1158**  
SUPPORT: **NITRILE VINYL FOAM**  
SUBSTRATE: **PAINTED METAL**  
CERT NO.: **221209 - 1310**

**FORD ESB-M11P8-A**  
OEM Rev Date: Jun 07  
Adhesion Requirements, PSA Sponge Rubber



### TAPE REQUIREMENTS:

#### 3 Standard Requirements for Production Materials

##### SECTION 3.1 Adhesion

3.1.1, As Received

ASTM D903

**Specification**

**0.66 N / mm**

**Results**

1.05

**Status**

**Pass**

##### SECTION 3.1 Adhesion

3.1.2.1, Aged, Heat Aged, 14 days @ 88°C

**Specification**

**0.22 N / mm**

**Results**

1.05

**Status**

**Pass**

##### SECTION 3.1 Adhesion

3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH

**Specification**

**0.44 N / mm**

**Results**

1.05

**Status**

**Pass**

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.