



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBR 1950
SUPPORT: EPDM FOAM
SUBSTRATE: PAINTED METAL
CERT NO.: 221209 - 1417



FORD ESB-M11P8-A
OEM Rev Date: Jun 07
Adhesion Requirements, PSA Sponge Rubber

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials

SECTION	3.1 Adhesion	ASTM D903	Specification	Results	Status
3.1.1, As Received			0.66 N / mm	.68 Tear	Pass

SECTION	3.1 Adhesion	ASTM D903	Specification	Results	Status
3.1.2.1, Aged, Heat Aged, 14 days @ 88°C			0.22 N / mm	0.38	Pass

SECTION	3.1 Adhesion	ASTM D903	Specification	Results	Status
3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH			0.44 N / mm	0.60	Pass

CERTIFIED BY:


Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.