



250 Chester Street  
Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 8327 12 PT BD  
SUPPORT: PET FOAM  
SUBSTRATE: PAINTED METAL  
CERT NO.: 221209 - 1422

**FORD ESB-M11P8-A**

OEM Rev Date: Jun 07

Adhesion Requirements, PSA Sponge Rubber  
Polyurethane Foam to Polypropylene - Pressure Sensitive Film



### TAPE REQUIREMENTS:

#### 3 Standard Requirements for Production Materials

##### SECTION 3.1 Adhesion

3.1.1, As Received

<u>Specification</u>	ASTM D903	<u>Results</u>	<u>Status</u>
0.66 N / mm		1.1	Pass

##### SECTION 3.1 Adhesion

3.1.2.1, Aged, Heat Aged, 14 days @ 88°C

<u>Specification</u>	<u>Results</u>	<u>Status</u>
0.22 N / mm	1.8	Pass

##### SECTION 3.1 Adhesion

3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH

<u>Specification</u>	<u>Results</u>	<u>Status</u>
0.44 N / mm	2.2	Pass

CERTIFIED BY:

\_\_\_\_\_  
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.