



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FBR 8950 12 PT BD  
SUPPORT: EPDM FOAM  
SUBSTRATE: PAINTED METAL  
CERT NO.: 221209 - 1312  
  
FORD ESB-M11P8-A  
OEM Rev Date: Jun 07  
Adhesion Requirements, PSA Sponge Rubber



### TAPE REQUIREMENTS:

#### 3 Standard Requirements for Production Materials

##### SECTION 3.1 Adhesion

3.1.1, As Received

Specification	ASTM D903	Results	Status
0.66 N / mm		0.91	Pass

##### SECTION 3.1 Adhesion

3.1.2.1, Aged, Heat Aged, 14 days @ 88°C

Specification	ASTM D903	Results	Status
0.22 N / mm		1.30	Pass

##### SECTION 3.1 Adhesion

3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH

Specification	ASTM D903	Results	Status
0.44 N / mm		1.09	Pass

CERTIFIED BY:

\_\_\_\_\_  
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.