



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: [psa.tape@averydennison.com](mailto:psa.tape@averydennison.com)  
URL: [tapes.averydennison.com](http://tapes.averydennison.com)

## TEST REPORT

PRODUCT: FT B 12 PT BD  
SUPPORT: NITRILE VINYL FOAM  
SUBSTRATE: SS  
CERT NO.: 221209 - 1305  
  
FORD ESB-M11P8-A  
OEM Rev Date: Jun 07  
Adhesion Requirements, PSA Sponge Rubber



### TAPE REQUIREMENTS:

#### 3 Standard Requirements for Production Materials

##### SECTION 3.1 Adhesion

3.1.1, As Received

ASTM D903-98 10

##### Specification

0.66 N / mm

##### Results

1.16

##### Status

Pass

##### SECTION 3.1 Adhesion

3.1.2.1, Aged, Heat Aged, 14 days @ 88°C

##### Specification

0.22 N / mm

##### Results

0.82

##### Status

Pass

##### SECTION 3.1 Adhesion

3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH

##### Specification

0.44 N / mm

##### Results

1.33

##### Status

Pass

CERTIFIED BY:



ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.