



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8392 12 PT BD
SUPPORT: 2 MIL PET
SUBSTRATE: PAINTED METAL
CERT NO.: 230109 - 1042

FORD ESB-M3G76-B2
OEM Rev Date: Sep 05
Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:

| SECTION | Test Description | ASTM D1000 | Specification | Results | Status |
|---------------|---|-----------------|---------------------------|----------------|--------|
| SECTION 3.6.1 | Peel Adhesion 3.6.1, Peel Adhesion, As Received, Initial RT | | 219 N / m | 1203.7 | Pass |
| SECTION 3.6.2 | Aged 3.6.2, Aged, Aged, 72 hrs @ RT | ASTM D1000 | 657 N / m | 1351.4 | Pass |
| SECTION 3.6.3 | Aged, Cycles 3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C | ASTM D1000 | 438 N / m | 1382.9 | Pass |
| SECTION 3.7 | Migration Stain 3.7, Migration Stain, 48 Hour Fluorescence, White Enamel | FLTM BO 115-01* | None | Not Applicable | NA |
| SECTION 3.8 | Liner Removal 3.8, Liner Removal, Initial Release | ASTM D1000 | 55 N / m | 17.5 | Pass |
| SECTION 3.9 | Storage Stability 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C | | No Appreciable Difference | Not Tested | TBD |

CERTIFIED BY:



Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.