



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8392
SUPPORT: 2 MIL PET
SUBSTRATE: PAINTED METAL
CERT NO.: 230109 - 1042

FORD ESB-M3G76-B2
OEM Rev Date: Sep 05
Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:

SECTION			<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6.1, Peel Adhesion, As Received, Initial RT	3.6.1 Peel Adhesion	ASTM D1000	219 N / m	1203.7	Pass
3.6.2, Aged, Aged, 72 hrs @ RT	3.6.2 Aged	ASTM D1000	657 N / m	1351.4	Pass
3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C	3.6.3 Aged, Cycles	ASTM D1000	438 N / m	1382.9	Pass
3.7, Migration Stain, 48 Hour Fluorescence, White Enamel	3.7 Migration Stain	FLTM BO 115-01*	None	Not Applicable	NA
3.8, Liner Removal, Initial Release	3.8 Liner Removal	ASTM D1000	55 N / m	25.1	Pass
3.9, Storage Stability, Liner Removal after 12 Months Below 32°C	3.9 Storage Stability		No Appreciable Difference	Not Tested	TBD

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.