



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBR 8950 12 PT BD
SUPPORT: PEU FOAM
SUBSTRATE: PAINTED METAL
CERT NO.: 221209 - 0853

FORD ESB-M3G76-B2
OEM Rev Date: Sep 05
Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:

SECTION			<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6.1, Peel Adhesion, As Received, Initial RT	3.6.1 Peel Adhesion	ASTM D3330	219 N / m	1947.4	Pass
3.6.2, Aged, Aged, 72 hrs @ RT	3.6.2 Aged	ASTM D3330	657 N / m	1950.9	Pass
3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C	3.6.3 Aged, Cycles	ASTM D3330	438 N / m	2262.1	Pass
3.7, Migration Stain, 48 Hour Fluorescence, White Enamel	3.7 Migration Stain	FLTM BO 115-1*	None	Not Applicable	NA
3.8, Liner Removal, Initial Release	3.8 Liner Removal	ASTM D3330	55 N / m	10.5	Pass
3.9, Storage Stability, Liner Removal after 12 Months Below 32°C	3.9 Storage Stability		No Appreciable Difference	Not Tested	TBD

CERTIFIED BY:


Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.