



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT B 12 PT BD
SUPPORT: EPDM FOAM
SUBSTRATE: PAINTED METAL
CERT NO.: 221209 - 0841

FORD ESB-M3G76-B2
OEM Rev Date: Sep 05
Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:

SECTION	Test Description	ASTM D3330	Specification	Results	Status
SECTION 3.6.1	Peel Adhesion 3.6.1, Peel Adhesion, As Received, Initial RT		219 N / m	840.0	Pass
SECTION 3.6.2	Aged 3.6.2, Aged, Aged, 72 hrs @ RT	ASTM D3330	657 N / m	1507.3	Pass
SECTION 3.6.3	Aged, Cycles 3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C	ASTM D3330	438 N / m	1039.7	Pass
SECTION 3.7	Migration Stain 3.7, Migration Stain, 48 Hour Fluorescence, White Enamel	FLTM BO 115-1*	None	Not Applicable	NA
SECTION 3.8	Liner Removal 3.8, Liner Removal, Initial Release	ASTM D3330	55 N / m	24.5	Pass
SECTION 3.9	Storage Stability 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C		No Appreciable Difference	Not Tested	TBD

CERTIFIED BY:



ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.