



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 8392  
SUPPORT: EPDM FOAM  
SUBSTRATE: PP  
CERT NO.: 221213 - 0744

**FORD ESH-M11P19-B**  
OEM Rev Date: Dec 13  
Adhesion Requirements, Cellular Rubber / Polyurethane Foam  
Pressure Sensitive Film with Biocide



### TAPE REQUIREMENTS:

#### 3 Requirements

##### SECTION 3.1 Peel Strength

3.1.1, As Received

Specification	ASTM D3330	Results	Status
0.44 N / mm		0.57	Pass

##### SECTION 3.1 Peel Strength

3.1.2, Aged, Heat Aged, 7 days @ 88°C

Specification	Results	Status
0.44 N / mm	0.59	Pass

##### SPEC: 3.1 Peel Strength

3.1.2, Humidity, 7 days @ 37°C / 95% RH

Specification	Results	Status
0.44 N / mm	0.63	Pass

##### SECTION 3.2 Peel Strength

3.2.1, Foam to Plastic Membrane, As Received

Specification	Results	Status
No Delamination	Foam Tearing	Pass

##### SECTION 3.3 Bond Separation

3.3, 200 gram load, 1 hr @ RT

Specification	Results	Status
No Separation of Bond	No Slip	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.