



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FBD 8970 12 PT BD  
SUPPORT: LOW PERM FOAM  
SUBSTRATE: ABS  
CERT NO.: 221213 - 0745

**FORD ESH-M11P19-B**

OEM Rev Date: Mar 93

Adhesion Requirements, Cellular Rubber / Polyurethane Foam  
Pressure Sensitive Film with Biocide



### TAPE REQUIREMENTS:

#### 3 Requirements

##### SECTION 3.1 Peel Strength

3.1.1, As Received

ASTM D3330

Specification

0.44 N / mm

Results

0.63

Status

Pass

##### SECTION 3.1 Peel Strength

3.1.2, Aged, Heat Aged, 7 days @ 88°C

ASTM D3330

Specification

0.44 N / mm

Results

1.41

Status

Pass

##### SECTION 3.1 Peel Strength

3.1.2, Humidity, 7 days @ 37°C / 95% RH

ASTM D3330

Specification

0.44 N / mm

Results

0.77

Status

Pass

##### SECTION 3.2 Peel Strength

3.2, Foam to Plastic Membrane, As Received

ASTM D3330

Specification

No Delamination

Results

Foam Tearing

Status

Pass

##### SECTION 3.3 Bond Separation

3.3, 200 gram load, 1 hr @ RT

ASTM D1000

Specification

No Separation of Bond

Results

No Slip

Status

Pass

##### SECTION 3.4 Quality

3.4, Quality

Specification

Readily Removable

Results

Easily Removed

Status

Pass

##### SECTION 3.5 Bacteria / Fungus Resistance

3.5, Bacteria / Fungus Resistance

Specification

Must Pass

Results

Not Tested

Status

NT

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.