



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8392 12 PT BD
SUPPORT: LOW PERM FOAM
SUBSTRATE: PP
CERT NO.: 221213 - 0755

FORD ESH-M11P40-A
OEM Rev Date: Sep 87
Adhesion Requirements
Pressure Sensitive Film with Biocide



TAPE REQUIREMENTS:

3 Requirements

SECTION	Test Description	Specification	ASTM D903	Results	Status
3.2	Peel Strength, Plastic Membrane to Panel 3.2.1, As Received	0.22 N / mm		1.16	Pass
3.2	Peel Strength, Plastic Membrane to Panel 3.2.2, Aged, Heat Aged, 7 days @ 88°C	0.22 N / mm	ASTM D903	1.15	Pass
3.2	Peel Strength, Plastic Membrane to Panel 3.2.2, Humidity, 7 days @ 37°C / 95% RH	0.11 N / mm	ASTM D903	0.96	Pass
3.3	Peel Strength 3.3.1, Foam to Plastic Membrane, As Received	No Delamination	ASTM D903	Foam Tearing	Pass
3.4	Bond Separation 3.4, 200 gram load, 1 hr @ RT	No Separation of Bond		No Slip	Pass
3.5	Quality 3.5, Quality	Readily Removable		Easily Removed	Pass
3.6	Bacteria / Fungus Resistance 3.6, Bacteria / Fungus Resistance	Must Pass		NGS - No Growth on Sample	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.