



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 8392 12 PT BD  
SUPPORT: PET FOAM  
SUBSTRATE: PAINTED METAL  
CERT NO.: 221213 - 0755

FORD ESH-M11P40-A  
OEM Rev Date: Sep 87  
Adhesion Requirements  
Pressure Sensitive Film with Biocide



### TAPE REQUIREMENTS:

#### 3 Requirements

SECTION	Test Description	Specification	ASTM D903	Results	Status
3.2	Peel Strength, Plastic Membrane to Panel 3.2.1, As Received	0.22 N / mm		2.08	Pass
3.2	Peel Strength, Plastic Membrane to Panel 3.2.2, Aged, Heat Aged, 7 days @ 88°C	0.22 N / mm	ASTM D903	2.08	Pass
3.2	Peel Strength, Plastic Membrane to Panel 3.2.2, Humidity, 7 days @ 37°C / 95% RH	0.11 N / mm	ASTM D903	1.44	Pass
3.3	Peel Strength 3.3.1, Foam to Plastic Membrane, As Received	Specification No Delamination	ASTM D903	Results Foam Tearing	Status Pass
3.4	Bond Separation 3.4, 200 gram load, 1 hr @ RT	Specification No Separation of Bond		Results No Slip	Status Pass
3.5	Quality 3.5, Quality	Specification Readily Removable		Results Easily Removed	Status Pass
3.6	Bacteria / Fungus Resistance 3.6, Bacteria / Fungus Resistance	Specification Must Pass		Results NGS - No Growth on Sample	Status Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.