



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 8392 EZ  
SUPPORT: PET FOAM  
SUBSTRATE: PAINTED METAL  
CERT NO.: 221213 - 0755

FORD ESH-M11P40-A  
OEM Rev Date: Sep 87  
Adhesion Requirements  
Pressure Sensitive Film with Biocide



### TAPE REQUIREMENTS:

#### 3 Requirements

SECTION 3.2 Peel Strength, Plastic Membrane to Panel  
3.2.1, As Received

Specification	ASTM D903	Results	Status
0.22 N / mm		2.08	Pass

SECTION 3.2 Peel Strength, Plastic Membrane to Panel  
3.2.2, Aged, Heat Aged, 7 days @ 88°C

Specification	ASTM D903	Results	Status
0.22 N / mm		2.08	Pass

SECTION 3.2 Peel Strength, Plastic Membrane to Panel  
3.2.2, Humidity, 7 days @ 37°C / 95% RH

Specification	ASTM D903	Results	Status
0.11 N / mm		1.44	Pass

SECTION 3.3 Peel Strength  
3.3.1, Foam to Plastic Membrane, As Received

Specification	ASTM D903	Results	Status
No Delamination		Foam Tearing	Pass

SECTION 3.4 Bond Separation  
3.4, 200 gram load, 1 hr @ RT

Specification	Results	Status
No Separation of Bond	No Slip	Pass

SECTION 3.5 Quality  
3.5, Quality

Specification	Results	Status
Readily Removable	Easily Removed	Pass

SECTION 3.6 Bacteria / Fungus Resistance  
3.6, Bacteria / Fungus Resistance

Specification	Results	Status
Must Pass	NGS - No Growth on Sample	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.