



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8392
SUPPORT: PEU FOAM
SUBSTRATE: PAINTED METAL
CERT NO.: 221213 - 0755

FORD ESH-M11P40-A
OEM Rev Date: Sep 87
Adhesion Requirements
Pressure Sensitive Film with Biocide



TAPE REQUIREMENTS:

3 Requirements

SECTION 3.2 Peel Strength, Plastic Membrane to Panel

3.2.1, As Received

Specification
0.22 N / mm

ASTM D903

Results
0.78

Status
Pass

SECTION 3.2 Peel Strength, Plastic Membrane to Panel

3.2.2, Aged, Heat Aged, 7 days @ 88°C

Specification
0.22 N / mm

ASTM D903

Results
1.05

Status
Pass

SECTION 3.2 Peel Strength, Plastic Membrane to Panel

3.2.2, Humidity, 7 days @ 37°C / 95% RH

Specification
0.11 N / mm

ASTM D903

Results
1.12

Status
Pass

SECTION 3.3 Peel Strength

3.3.1, Foam to Plastic Membrane, As Received

Specification
No Delamination

ASTM D903

Results
Foam Tearing

Status
Pass

SECTION 3.4 Bond Separation

3.4, 200 gram load, 1 hr @ RT

Specification
No Separation of Bond

Results
No Slip

Status
Pass

SECTION 3.5 Quality

3.5, Quality

Specification
Readily Removable

Results
Easily Removed

Status
Pass

SECTION 3.6 Bacteria / Fungus Resistance

3.6, Bacteria / Fungus Resistance

Specification
Must Pass

Results
Not Tested

Status
Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.