



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: [psa.tape@averydennison.com](mailto:psa.tape@averydennison.com)  
URL: [tapes.averydennison.com](http://tapes.averydennison.com)

## TEST REPORT

PRODUCT: **FBR 8950**  
SUPPORT: **PET FOAM**  
SUBSTRATE: **PAINTED METAL**  
CERT NO.: 221213 - 0807

**FORD WSA-M11P19-C**  
OEM Rev Date: Jul 93  
Adhesion Requirements, Polyurethane Foam  
Pressure Sensitive Adhesive, High Tack



### TAPE REQUIREMENTS:

#### 3 Requirements

##### SECTION 3.4 Peel Strength

3.4.1, As Received

<u>Specification</u>	ASTM D3330	<u>Results</u>	<u>Status</u>
<b>0.88 N / mm</b>		1.94	Pass

##### SECTION 3.4 Peel Strength

3.4.2, Heat Aged, 7 days @ 88°C

<u>Specification</u>	ASTM D3330	<u>Results</u>	<u>Status</u>
<b>0.88 N / mm</b>		2.00	Pass

##### SECTION 3.4 Peel Strength

3.4.2, Humidity, 7 days @ 37°C / 95% RH

<u>Specification</u>	ASTM D3330	<u>Results</u>	<u>Status</u>
<b>0.88 N / mm</b>		1.92	Pass

##### SECTION 3.5 Peel Strength

3.5.1, Foam to Plastic Membrane, As Received

<u>Specification</u>	ASTM D3330	<u>Results</u>	<u>Status</u>
<b>Foam Tear</b>		Foam Tearing	Pass

##### SECTION 3.5 Creep Adhesion

3.6, 200 gram load, 1 hr @ RT

<u>Specification</u>		<u>Results</u>	<u>Status</u>
<b>&lt; 6.4 mm</b>		No Slip	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.