



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: [psa.tape@averydennison.com](mailto:psa.tape@averydennison.com)  
URL: [tapes.averydennison.com](http://tapes.averydennison.com)

## TEST REPORT

PRODUCT: FT 8714  
SUPPORT: EPDM FOAM  
SUBSTRATE: PAINTED METAL  
CERT NO.: 221213 - 0808



### FORD WSB M3G102-B

OEM Rev Date: Standard Requirements for Production Materials  
B - Tape, Low Density PVC Foam , Pressure Sensitive, Supersoft  
Soft, Closed Cell PVC Foam Tape with One Side Adhesive  
Coated And The Other Side Protected By A Coated Release

#### TAPE REQUIREMENTS:

SECTION: 3.12 Pressure Sensitive Adhesion	ASTM D1000	Specification	Results	Status
3.12.1, Adhesion to Stainless Steel, Initial Room Temp		440 N / m	1159.9	Pass
SECTION: 3.12 Pressure Sensitive Adhesion		Specification	Results	Status
3.12.2, Adhesion to Painted Metal, Initial Room Temp		440 N / m	1117.9	Pass
SECTION: 3.12 Pressure Sensitive Adhesive		Specification	Results	Status
3.12.3, Adhesion to Stainless Steel, Heat Resistance, 30 mins @ 120°		No Adhesion Failure	Good, Stable, No lifting or Adhesion Loss	Pass
SECTION: 3.12 Pressure Sensitive Adhesive		Specification	Results	Status
3.12.3, Adhesion to Stainless Steel, Cycling Resistance, 5X, Flat 16 hrs @ 38° C / 95% RH 4 hrs @ -29° C 4 hrs @ 82° C		No Adhesion Failure	Good, Stable, No lifting or Adhesion Loss	Pass
SECTION: 3.13 Liner Release	ASTM D3330	Specification	Results	Status
3.12 Initial Room Temp		11 N / m	8.8	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.