



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT B 12 PT BD
SUPPORT: RUBBER
SUBSTRATE: PAINTED METAL
CERT NO.: 221213 - 0811

FORD WSF-M11P8-A2
OEM Rev Date: Jan 92
Adhesion Requirements



Sponge Rubber, High Tack

TAPE REQUIREMENTS:

3 Requirements

SECTION 3.3 Adhesion

3.3.1, As Received

ASTM D903

Specification

0.88 N / mm

Results

1.19

Status

Pass

SECTION 3.3.2 Adhesion
3.3.2.1, Heat Aged, 14 days @ 88°C

ASTM D903

Specification

0.33 N / mm

Results

0.96

Status

Pass

SECTION 3.3.2 Adhesion
3.3.2.1, Humidity, 14 days @ 37°C / 95% RH

ASTM D903

Specification

0.66 N / mm

Results

1.73

Status

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.