



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 1126 12 PT BD  
SUPPORT: FABRIC  
SUBSTRATE: TALC FILLED PP  
CERT NO.: 221213 - 0855

### FORD WSS-M11P62-A

OEM Rev Date: Jul 05

Performance Requirements for Adhesives Used in Interior Applications  
Assembly Performance Parts At or Above the Belt Line



#### TAPE REQUIREMENTS:

SECTION: 3.5 Odor  
3.5, Odor

SAE J1351\*      Specification  
                    2 Rating

Results  
Not Tested      Status  
NT

SECTION: 3.4 Flammability  
3.4, Flammability, Initial, Component

SAE J369      Specification  
                    100 mm / min

Results  
EBRZT      Status  
Pass

SECTION: 3.6 Fogging  
3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT

SAE J1756      Specification  
                    70 Units

Results  
79.4      Status  
Pass

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

70 Units

70.0

Pass

CERTIFIED BY:

\_\_\_\_\_  
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.