



250 Chester > 70 Units  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 3043  
SUPPORT: 5 MIL BLACK UHMWPE  
SUBSTRATE: TPO  
CERT NO.: 221213 - 0901

**FORD WSS-M11P62-A**

OEM Rev Date: Jun 07

Performance Requirements for Adhesives Used in Interior Applications  
Assembly Performance Parts Below the Belt Line



### TAPE REQUIREMENTS:

SECTION: 3.4 Flammability	ISO 3795 / SAE J369	Specification	Results	Status
3.4, Initial, Component		100 mm / min	< B 25	Pass

SECTION: 3.5 Odor	SAE J1351	Specification	Results	Status
3.5 Odor, 1 hr @ 65°C - Dry		2 Rating	2 - Slight, But Noticeable Odor	Pass

3.5 Odor, 1 hr @ 65°C - Wet	2 Rating	2 - Slight, But Noticeable Odor	Pass
-----------------------------	----------	---------------------------------	------

SECTION: 3.6 Fogging	SAE J1756	Specification	Results	Status
3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT		> 70 Units	103.5	Pass

3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT	> 70 Units	101.7	Pass
---	------------	-------	------

CERTIFIED BY:

\_\_\_\_\_  
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.