



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 8327 12 PT BD  
SUPPORT: PET FABRIC  
SUBSTRATE: 40% TALC PP  
CERT NO.: 221213 - 0911

FORD WSS-M11P62-A

OEM Rev Date: Jul 05

Performance Requirements for Adhesives Used in Interior Applications  
Assembly Performance Parts Below the Belt Line



### TAPE REQUIREMENTS:

SECTION: 3.5 Odor

3.5 Odor, 1 hr @ 65°C - Dry

SAE J1351\*

Specification

2 Rating

Results

2 - Slight, But Noticeable Odor

Status

Pass

3.5 Odor, 1 hr @ 65°C - Wet

2 Rating

2 - Slight, But Noticeable Odor

Pass

SECTION: 3.4 Flammability

3.4, Flammability, Initial, Component

SAE J369

Specification

100 mm / min

Results

< B 25

Status

Pass

SECTION: 3.6 Fogging

3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT

SAE J1756

Specification

70 Units

Results

84.1

Status

Pass

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

70 Units

100.9

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.