



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8392 12 PT BD
SUPPORT: RED FLOCK
SUBSTRATE: E-COATED METAL
CERT NO.: 221213 - 0912

FORD WSS-M11P62-A

OEM Rev Date: Jun 07

Performance Requirements for Adhesives Used in Interior Applications



TAPE REQUIREMENTS:

SECTION: 3.4 Flammability

SAE J369

Specification

100 mm / min

Results

EBRZT

Status

Pass

3.4, Initial, Component

SECTION: 3.5 Odor

SAE J1351*

Specification

2 Rating

Results

2 - Slight, But Noticeable Odor

Status

Pass

3.5 Odor, 1 hr @ 65°C - Dry

3.5 Odor, 1 hr @ 65°C - Wet

2 Rating

2 - Slight, But Noticeable Odor

Pass

SECTION: 3.6 Fogging

SAE J1756

3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT

Specification

70 Units

Results

98.1

Status

Pass

3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

70 Units

98.7

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.