



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: [psa.tape@averydennison.com](mailto:psa.tape@averydennison.com)  
URL: [tapes.averydennison.com](http://tapes.averydennison.com)

## TEST REPORT

PRODUCT: FBA 8960 12 PT BD  
SUPPORT: PET FOAM  
SUBSTRATE: PC ABS  
CERT NO.: 221213 - 1016

FORD WSS-M11P68-A1

OEM Rev Date: Jan 20

Tape, Performance, Pressure Sensitive Adhesive One-Sided, Interior  
Scuff Plate / Floor Area



### TAPE REQUIREMENTS:

#### 3. Requirements

SECTION: 3.5 Thickness  
3.5 Thickness

FLTM BO 131-03*	Specification	Results	Status
	Reported mm	44.87	Reported

SECTION: 3.6 Weight  
3.6 Weight

FLTM BO 131-03*	Specification	Results	Status
	Reported g / m <sup>2</sup>	5.305	Reported

SECTION: 3.7 Breaking Strength  
3.7 Breaking Strength

FLTM BO 131-03*	Specification	Results	Status
	Reported N / 10 mm	20.16	Reported

#### 3.8 Fogging

3.8 Fogging - Photometric, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

FLTM BO 131-03*	Specification	Results	Status
	70 Units min	96	Pass

#### 3.9 Odor

3.9.1 Odor, Condition 1 - 24 hrs @ RT, Deionized Water

FLTM BO 131-03*	Specification	Results	Status
	Rating 3 Max	Not Perceptible, 1	Pass

3.9.2 Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water

	Rating 3 Max	Not Perceptible, 1	Pass
--	--------------	--------------------	------

3.9.3 Odor, Condition 3 - 2 hrs @ 65°C

	Rating 3 Max	Perceptible, Not Disturbing, 2	Pass
--	--------------	--------------------------------	------

#### 3.10 Flammability

3.2.3 Initial, Component

SAE J369*	Specification	Results	Status
	< 100 mm / min	< B 25	Pass

#### 3.11 Adhesion Strength

3.11 Original

ASTM D1000	Specification	Results	Mode	Status
	300 N / m	1385.4	CSP	Pass

3.11.2 After Short Term Environment Cycling

5 hrs @ -30°C  
30 mins @ 23°C / 50%RH  
5 hrs @ 80°C  
30 mins @ 23°C / 50%RH  
2 hrs @ 50°C / 95%RH  
30 mins @ 23°C / 50%RH  
5 hrs @ -30°C  
30 mins @ 23°C / 50%RH  
5 hrs @ 80°C

FLTM BO 140-01 A*	225 N / m	1037.8	CSP	Pass
-------------------	-----------	--------	-----	------

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

FLTM BO 140-01 B*	225 N / m	1093.8	CSP	Pass
-------------------	-----------	--------	-----	------

#### 3.11 Adhesion Strength

3.11 Original

Specification	Results	Status
No Cracking, Blistering, Adhesion Loss or Delamination	Good, Stable, No Defects or Lifting	Pass

3.11.2 After Short Term Environment Cycling

Specification	Results	Status
No Cracking, Blistering, Adhesion Loss or Delamination	Good, Stable, No Defects or Lifting	Pass

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

Specification	Results	Status
No Cracking, Blistering, Adhesion Loss or Delamination	Good, Stable, No Defects or Lifting	Pass

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.  
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.