



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBA 8960 12 PT BD
SUPPORT: PEU FOAM
SUBSTRATE: PC ABS
CERT NO.: 221213 - 1016

FORD WSS-M11P68-A1

OEM Rev Date: Jan 20

Tape, Performance, Pressure Sensitive Adhesive One-Sided, Interior
Scuff Plate / Floor Area



TAPE REQUIREMENTS:

3. Requirements

SECTION: 3.5 Thickness
3.5 Thickness

FLTM BO 131-03*	Specification	Results	Status
	Reported mm	40.33	Reported

SECTION: 3.6 Weight
3.6 Weight

FLTM BO 131-03*	Specification	Results	Status
	Reported g / m ²	5.304	Reported

SECTION: 3.7 Breaking Strength
3.7 Breaking Strength

FLTM BO 131-03*	Specification	Results	Status
	Reported N / 10 mm	20.04	Reported

3.8 Fogging

3.8 Fogging - Photometric, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

FLTM BO 131-03*	Specification	Results	Status
	70 Units min	96	Pass

3.9 Odor

3.9.1 Odor, Condition 1 - 24 hrs @ RT, Deionized Water

FLTM BO 131-03*	Specification	Results	Status
	Rating 3 Max	Not Perceptible, 1	Pass

3.9.2 Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water

	Rating 3 Max	Not Perceptible, 1	Status
			Pass

3.9.3 Odor, Condition 3 - 2 hrs @ 65°C

	Rating 3 Max	Slightly Perceptible, 1.5	Status
			Pass

3.10 Flammability

3.2.3 Initial, Component

SAE J369*	Specification	Results	Status
	< 100 mm / min	< B 25	Pass

3.11 Adhesion Strength

3.11 Original

ASTM D1000	Specification	Results	Mode	Status
	300 N / m	1097.8	CSP	Pass

3.11.2 After Short Term Environment Cycling

5 hrs @ -30°C
30 mins @ 23°C / 50%RH
5 hrs @ 80°C
30 mins @ 23°C / 50%RH
2 hrs @ 50°C / 95%RH
30 mins @ 23°C / 50%RH
5 hrs @ -30°C
30 mins @ 23°C / 50%RH
5 hrs @ 80°C

FLTM BO 140-01 A*	225 N / m	704.7	L CSP	Status
-------------------	-----------	-------	-------	--------

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

FLTM BO 140-01 B*	225 N / m	1059.3	L CSP	Status
-------------------	-----------	--------	-------	--------

3.11 Adhesion Strength

3.11 Original

Specification	Results	Status
---------------	---------	--------

3.11.2 After Short Term Environment Cycling

No Cracking, Blistering, Adhesion Loss or Delamination	Good, Stable, No Defects or Lifting	Pass
--	-------------------------------------	------

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

	Good, Stable, No Defects or Lifting	Pass
--	-------------------------------------	------

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.